

参数(Parameter)	符号(Symbol)	单位(Unit)	测试条件(Condition)			MP332A
			Freq.	Fluxden.	Temp.	
初始磁导率 (Initial Permeability)	μ_i	/	100KHz	100mv	23°C	3300±25%
功耗 (Power-loss)	P_{cv}	KW/m^3	100KHz	200mT	23°C	290
					100°C	280
					120°C	320
					23°C	540
饱和磁通密度 (Saturation Flux Density)	B_s	mT	50Hz	1194A/m	100°C	430
剩磁 (Residual Flux Density)	B_r	mT	50Hz	1194A/m	23°C	80
					100°C	70
居里温度 (Curie Temperature)	T_c	°C				220
电阻率 (Electrical Resistivity)	ρ	Ωm				5
密度 (Density)	d	g/cm^3				4.9

说明:以上性能采用 $\varnothing 13.4 \times \varnothing 6.7 \times 5.4$ 磁环, 在不加外力的情况下测试, 不同产品在特性表现上略有差异。

Note: Measured on sintered, non-ground ring cores of dimensions $\varnothing 13.4 \times \varnothing 6.7 \times 5.4$ which are not subjected to external stresses. Product specification will differ from these data due to the influence of geometry and size.

