

| 参数(Parameter) | 符号(Symbol) | 单位(Uint) | 测试条件(Condition) | | | MT402 |
|--|------------------|----------------------------|-----------------|----------|---------|----------|
| | | | Freq. | Fluxden. | Temp. | |
| 初始磁导率 (Initial IPermeability) | μ_i | / | 10kHz | 100mv | 23°C | 4000±25% |
| 相对损耗因子 (Relative Loss Factor) | $\tan\delta/\mu$ | 10^{-6} | 10kHz | 50mV | 23°C | <8 |
| | | | 100kHz | 50mV | 23°C | <30 |
| 饱和磁通密度 (Saturation Flux Density) | B_s | mT | 50Hz | 1194A/m | 23°C | 470 |
| | | | | | 100°C | 360 |
| 剩磁 (Residual Flux Density) | B_r | mT | 50Hz | 1194A/m | 23°C | 60 |
| | | | | | 100°C | 50 |
| 温度系数 (Temperature Factor of Permeability) | α_F | $10^{-6}/^{\circ}\text{C}$ | 10KHz | 50mV | 0~20°C | -0.5~0.5 |
| | | | | | 20~70°C | 0~1 |
| 居里温度 (Curie Temperature) | T_c | °C | | | | 170 |
| 电阻率 (Electrical Resistivity) | ρ | Ωm | | | | 1 |
| 密度 (Density) | d | g/cm^3 | | | | 4.9 |

说明:以上性能采用 $\varnothing 13.4 \times \varnothing 6.7 \times 5.4$ 磁环, 在不加外力的情况下测试, 不同产品在特性表现上略有差异。

Note:Measured on sintered, non-ground ring cores of dimensions $\varnothing 13.4 \times \varnothing 6.7 \times 5.4$ which are not subjected to external stresses. Product specification will differ from these data due to the influence of geometry and size.

